

GENERAL REQUIREMENTS

- A.** Inland products can only be applied to a sound surface, which is free of structural problems and defects. All Inland Application Specifications assume that the insulation is free of moisture and in good condition.
- B.** Install all materials in strict accordance with all published safety, weather, or applicable regulation of the manufacturer and/or local, state and/or federal agency which has jurisdiction.
- C.** All surfaces must be clean and dry at each stage of application: Free of dirt, debris, droppings, oily residues or moisture.
- D.** Treat mold, mildew, or other organic growth with a mixture of 1/3 cup detergent combined with 1 gallon of non-ammoniated bleach and 2 gallons of water. Let stand 10 to 30 minutes and rinse.
- E.** Treat new metal with Tri-Sodium Phosphate.
- F.** All products should be thoroughly mixed prior to use.

WEATHER CONDITIONS

- A.** Ambient air temperature must be between 45° to 100°F.
- B.** Application shall not begin during inclement weather or when precipitation appears imminent.
- C.** Complete curing is 21 days under normal weather conditions.
- D.** Should ponding occur before curing, blow or sweep water from the surface to allow curing. The physical properties of Inland products can be severely diminished if sufficient drainage is not provided prior to curing.

MAINTENANCE

- A.** Check roof every 6 (six) months for structural damage and remove accumulated debris from roof and gutters.
- B.** Inspect coated surface on an annual basis.

WARRANTY

- A.** The Inland Metal Roof System Warranty is available only when the roof system is installed by an Inland Approved Roofing Contractor.
- B.** The Inland Roof System does not include the roof insulation, roof deck, vapor retarder, or any roof accessories.