



RS 2030

Roof Sealer

RS 2030 is a clear, flexible coating for use on Modified Bitumen and asphaltic surfaces. It prevents bleed and discoloration, providing improved color and dramatically lower roof temperatures when top-coated with RC 2000 Rubber Roof Coating.

TYPE OF APPLICATIONS:

- Asphaltic Surfaces
- Builtup Roofing
- Modified Bitumen

RS 2030 is a one-component product; can be sprayed or brushed; requires minimal surface preparation; has excellent adhesion to properly prepared surfaces.

RS 2030's added protection reduces costly re-applications.

PRODUCT TEMPERATURE:

For best spray application, the product should be at a minimum of 60°F before spraying. RS-2030 should not be allowed to freeze.

APPLICATION TEMPERATURE:

For best results, the temperature of the ambient air and the substrate should be within a range of 50°-110°F.

APPLICATION METHODS:

RS-2030 can be applied by brush, spray or roller. Best results can be obtained with airless spray equipment. See Inland Application Bulletins for additional information.

Recommended Spray Equipment = Airless
 Tip size019"
 Fluid Pressure(PSI). . . . 2000
 Fluid hose size 3/8" – 1/2"

Color Clear
 Coverage Rate. 250 SF/gal
 Wet Mil Thickness 6 – 8 mils
 Dry Mil Thickness 3 – 4 mils
 Flashpoint None
 Specific Gravity 1.02
 Weight (lb./gal.) 8.5
 Solids (% by Weight) 44.1 ±1%
 Viscosity @ 78° 1400 cps.
 Drying Time 1 – 3 hours

SURFACE PREPARATION:

The surface must be clean, dry and free of dirt, oil or other contaminants prior to application. This is normally best achieved by power washing the surface. Spray nozzle should be held an adequate distance from the surface to prevent roof damage. Make sure all drains are free of debris or blockage. Allow roof to dry thoroughly before any product applications.

RS 2030 HANDLING & STORAGE:

Store in a cool, dry, well-ventilated area. Avoid Freezing. Do not get into eyes. Avoid prolonged breathing of vapors or repeated skin contact. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

Form:#LC2030-8 Revision:02/18