



RC 2013M

Metal Base Coat

RC 2013M is a rubber base-coat that provides excellent waterproofing and corrosion resistance to metal roof surfaces. It is a one-component product that has excellent adhesion to properly prepared surfaces. RC 2013M is thermally stable and resists cracking and peeling due to weather extremes. For long-term ultraviolet exposure, RC 2013M must be top-coated with RC 2014T Rubber Roof Coating.

TYPE OF APPLICATIONS:

- Metal Roofing and surfaces

SURFACE PREPARATION:

The surface must be free of any oils, moisture, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces. Oil and grease should also be removed with solvents or an appropriate detergent cleaner. In many cases high pressure water blast will be sufficient to prepare the surface.

APPLICATION TEMPERATURES:

For best results, the temperature of the ambient air and the substrate should be within a range of 50°-100°F. For best spray application, the product should be at a minimum of 60°F. Lower temperatures can be utilized for brush applications.

APPLICATION METHODS:

RC 2013M can be applied by brush, spray or roller. Best results can be obtained with airless spray equipment. See Inland Application Bulletins for additional information.

Recommended Spray Equipment = Airless

- Tip size025"
- Fluid Pressure (PSI). . . . 3000
- Fluid hose size 3/8" - 1/2"

TECHNICAL DATA:

- Coverage Rate. 65-100 sf/gal
- Flashpoint 101°F.
- Weight (lb./gal.) 8.3
- Solids (% by Weight) 50.0±1%
- Viscosity @ 78° 4000 cps.
- Drying Time 2-4 hours
- Elongation. 400%
- Tensile Strength ASTM-D-412 . 1500 PSI

HANDLING & STORAGE:

RC 2013M contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

Form:#LC2013-M Revision:02/18