

**SEBS SEALANT SB** *Universal Thermoplastic Sealant***DESCRIPTION:**

SEBS Sealant SB is a high-performance, multipurpose thermoplastic construction sealant. It is used to seal seams, flashings and penetrations on all types of roof surfaces. Excellent adhesion to most surfaces including: metal, Kynar®, asphalt, shingles, modified bitumen, EPDM, TPO, Elvaloy/PVC, Hypalon, vinyl, fiber cement, wood, concrete, tile, masonry and glass. Ideal for applications where appearance is important.

- Low dirt pickup
- Bonds to most common building substrates
- Remains flexible to absorb expansion and contraction
- Ideal for residential or commercial roofing

**INSTALLATION INSTRUCTION:**

**SURFACE PREPARATION:** Remove all previous sealant, coatings, or other repair materials from the joint or surface. Clean to remove dirt, grease, oil, and other contaminants. If compatible with the substrate, solvents such as virgin mineral spirits or VM&P naphtha may be used. Allow the surface to dry completely before application.

**APPLICATION INSTRUCTIONS:** Maintain product temperature at 70 °F (21 °C) or above before and during application for best results. Joints should not exceed 3/8 inch in width or depth. For deeper joints, use a backer rod. Cut the nozzle to the desired bead size, puncture the inner seal, and apply a continuous bead with a quality caulking gun, ensuring full contact with both joint sides. Tool to a smooth finish and remove excess before skinning occurs. Coverage is approximately 26 lineal feet per 10.1 oz cartridge at a 1/4-inch bead. SEBS Sealant SB can be painted after 48 hours; some paints may require up to one week of cure time before application.

**PACKAGING:**

10.1oz Plastic Tube	24 per box	45 boxes (1080 tubes)/pallet
---------------------	------------	------------------------------

**TECHNICAL DATA:**

VOC	EPA 24	<300 g/L
Solids by Weight	ASTM D 1644	73%
Solids by Volume	ASTM D 2697	68%
Weight Per Gallon	ASTM D 1147	8.8 lbs.
Tensile Strength	ASTM D 2370	700 psi
Elongation	ASTM D 2370	1000%
Movement	ASTM C 719	+/-25%
Skin Time	ASTM C 679	30 Minutes
Tack Free	ASTM C 679	3 Hours
Flash Point	ASTM D 56	103°F / 39°C
Colors	White, Gray, Black, Bronze, Clear	

**PRECAUTIONS:**

- SEBS Sealant SB usually does not require a primer, but some substrates may need one for a lasting, weatherproof bond. The applicator must determine if a primer is required.
- Cold material, a small nozzle opening, or an incompletely punctured inner seal may result in blowout at the back of the cartridge.
- Avoid application when freezing temperatures, rain, high humidity, dew, or condensation are expected within 8-hours after application, as these conditions may interfere with proper curing.

**STORAGE & HANDLING PROCEDURES:**

Store locked up. Store in a well-ventilated place. Shelf life is 12-months if stored in original unopened containers. Store between 45°F and 95°F. Do not heat with an open flame. All containers must be sealed when not in use. Wear protective gloves, protective clothing, eye protection, and face protection. If exposed or concerned: Get medical advice or attention.

**WARRANTY & DISCLAIMER:**

Inland Coatings, Inc. (Inland) warrants that this product conforms to the published product specifications as of the date of manufacture. Inland does not make, nor does it authorize anyone to make, any warranty of merchantability or fitness for any purpose, or any other warranty, guarantee, or representation. INLAND HEREBY DISCLAIMS ANY AND ALL EXPRESS, IMPLIED, OR STATUTORY WARRANTIES. The sole obligation of the manufacturer, distributor, and/or seller of this product shall be the replacement of product proven to be defective in manufacturing if written notice is received within one year of the date of purchase. There shall be no liability for injury, loss, or damages, either direct or consequential, arising out of the use or inability to use this product. Failure to notify the manufacturer prior to remedy or resolution voids the warranty and the manufacturer's liability.