

Fabric Polyester Reinforcing Fabric**DESCRIPTION:**

Inland Fabric is a high-quality fabric utilized to reinforce seams, cracks, and roofing penetrations in tandem with various roof coating mastic and repair products. The stitch bonded fabric is a great option when wanting to reinforce many areas on a roof.

SUITABLE SUBSTRATES:

- EPDM
- PVC
- Hypalon
- TPO
- BUR (asphalt)
- Modified Bitumen
- Metal
- New Spray Polyurethane Foam

INSTALLATION INSTRUCTIONS:

SURFACE PREPARATION: The surface must be free of any oils, moisture, rust scale, soil or other contaminants that may interfere with good adhesion. All previous repair material must be removed from seams or other surfaces. In many cases high pressure water blast will be sufficient to prepare the surface.

APPLICATION INSTRUCTIONS: Apply only when ambient temperatures are 50°F and rising, and substrate temperatures do not exceed greater than 110°F. Apply coating at least 6 inches wide, centered over the seam or repair area. Then cut the desired length and immediately embed a 4 inch strip of fabric into the wet coating, ensuring it is centered over the seam. Use a dry brush to work the fabric into the coating until fully saturated. Allow coating to dry to touch and apply a second layer of coating to fully encapsulate the fabric.

PACKAGING:

4" Fabric	4" x 300'
6" Fabric	6" x 300'
40" Fabric	40" x 324'

TECHNICAL DATA:	VALUE:	TEST METHOD / STANDARD:
Weight per Square Yard	4 oz	
Ball Burst	66.3	ASTM D3787
Tensile Strength	47.4 PSI - MD 44.5 PSI - CD	ASTM D5034
Trapezoid Tear	12.6 lbs - MD 17.7 lbs - CD	ASTM D5587
Elongation	16.2 lbs - MD 46.9 lbs - CD	ASTM D5034
Thickness	0.024 inches	ASTM D1777

PRECAUTIONS:

- Fabric must be smooth, free of wrinkles and blisters.
- Fabric must be fully encapsulated.

HANDLING & STORAGE PROCEDURES:

Shelf life is 24-months if stored in original unopened containers. Store between 45°F and 95°F. Do not allow product to freeze. Do not heat with an open flame. Wear protective gloves, protective clothing, eye protection, and face protection.

WARRANTY & DISCLAIMER:

Inland Coatings, Inc. (Inland) warrants that this product conforms to the published product specifications as of the date of manufacture. Inland does not make, nor does it authorize anyone to make, any warranty of merchantability or fitness for any purpose, or any other warranty, guarantee, or representation. INLAND HEREBY DISCLAIMS ANY AND ALL EXPRESS, IMPLIED, OR STATUTORY WARRANTIES. The sole obligation of the manufacturer, distributor, and/or seller of this product shall be the replacement of product proven to be defective in manufacturing if written notice is received within one year of the date of purchase. There shall be no liability for injury, loss, or damages, either direct or consequential, arising out of the use or inability to use this product. Failure to notify the manufacturer prior to remedy or resolution voids the warranty and the manufacturer's liability.

