

# ALDOSIL 395 Low-Solids Silicone Roof Coating



## TECHNICAL DATA:

|                             |                         |              |
|-----------------------------|-------------------------|--------------|
| Solids by Weight            | 82%                     | ASTM D1644   |
| Solids by Volume            | 68%                     | ASTM D2697   |
| Weight (lb/gal)             | 11.3 lbs                | ASTM D1475   |
| Elongation                  | 186%                    | ASTM D412    |
| Tensile Strength            | 551 psi                 | ASTM D412    |
| VOC Content                 | 246 g/L                 |              |
| Solar Reflectance (Initial) | 0.87                    | (White Only) |
| Thermal Emittance (Initial) | 0.90                    | (White Only) |
| SRI Value (Initial)         | 113                     | (White Only) |
| Shelf Life                  | 24-months               |              |
| Standard Color(s)           | White, Tan, Gray, Black |              |

All tests were performed by independent laboratories on randomly collected samples. Results may vary by  $\pm 10\%$ . This data supersedes all previously published information.

## PACKAGING:

|                   |         |               |
|-------------------|---------|---------------|
| 5-Gal Metal Pail  | 60 lbs  | 36 Per Pallet |
| 50-Gal Metal Drum | 640 lbs | 4 Per Pallet  |

## PRECAUTIONS:

- Cure times will be faster in humid climates and slower in dry climates.
- Open containers will skin over if not applied quickly enough. If this happens, remove the skin and continue with application.
- For steep slope applications, the coverage rate may need to be reduced, and multiple coats may be required.
- For cooler weather applications, products must be stored at room temperature prior to installation.
- When spraying, do not use hoses that have been previously used for acrylics.
- Product may discolor if applied without a bleed-blocking primer.

## HANDLING & STORAGE PROCEDURES:

Shelf life is 24-months if stored in original unopened containers. Store between 45°F and 95°F. Do not heat with an open flame. All containers must be sealed when not in use. Wear protective gloves, protective clothing, eye protection, and face protection. If exposed or concerned: Get medical advice or attention. Clean equipment and any overspray with virgin mineral spirits. Do not thin or self-tint.

## DESCRIPTION:

AldoSil 395 is a solvent-based, moisture-curing silicone roof coating engineered to provide long-lasting protection across a variety of roofing surfaces. It offers strong resistance to harsh weather, UV exposure, and water intrusion. Known for its superior adhesion and ability to fill voids and surface imperfections, it is a preferred choice for spray foam roofs.

## APPROVED SUBSTRATES:

- Metal
- Aged EPDM
- Aged TPO
- Aged PVC
- Smooth BUR (asphalt)
- Smooth & Granulated Modified Bitumen
- Concrete
- New Spray Polyurethane Foam

## INSTALLATION INSTRUCTIONS:

**SURFACE PREPARATION:** The surface must be free of any oils, moisture, rust scale, soil or other contaminants that may interfere with good adhesion. All previous repair material must be removed from seams or other surfaces. To prevent staining from asphalt-based roofing substrates, use AldoBlock 708 as a primer barrier.

**APPLICATION INSTRUCTIONS:** Mix thoroughly before application. Avoid entraining air while mixing. Apply only when ambient temperatures are 50°F and rising, and substrate temperatures do not exceed greater than 130°F. For optimal spray application, the product temperature should be above 60°F. Lower temperatures can be utilized for brush/rolling applications. The typical minimum application requires two coats at 16 wet mils. Application rates may vary depending on the substrate and the warranty term.



**LIMITED WARRANTY:**

Inland Coatings, Inc. (Inland) warrants that this product conforms to the published product specifications as of the date of manufacture. Inland does not make, nor does it authorize anyone to make, any warranty of merchantability or fitness for any purpose, or any other warranty, guarantee, or representation. INLAND HEREBY DISCLAIMS ANY AND ALL EXPRESS, IMPLIED, OR STATUTORY WARRANTIES. The sole obligation of the manufacturer, distributor, and/or seller of this product shall be the replacement of product proven to be defective in manufacturing if written notice is received within one year of the date of purchase. There shall be no liability for injury, loss, or damages, either direct or consequential, arising out of the use or inability to use this product. Failure to notify the manufacturer prior to remedy or resolution voids the warranty and the manufacturer's liability.